



**Advanced Epoxy  
TECHNOLOGY**  
for more durability

# DRYLOK®

## E1 1-PART EPOXY FLOOR PAINT

**Concrete Steps  
& Walkways**

**Concrete Surfaces  
& Garage Floors**

**Concrete Laundry  
Rooms & Basements**

**Interior/Exterior • Ready-to-Use • High Traffic Formula •  
Resists Hot Tire Pick-up & Staining • Excellent Chemical Resistance •  
Protects & Beautifies Concrete Floors • Soap & Water Clean-up**

### READY-MIXED COLORS

**NATURAL SAND**

**SLATE GRAY**

**ARCTIC WHITE**

**LIGHT PLATINUM**



**UGL®**

# DRYLOK

## E1 1-PART EPOXY FLOOR PAINT




### UGL® DRYLOK® 1-Part Epoxy Floor Paint

Whether you want to renew old concrete or impart a decorative style to lighten up a dark and dingy space, E1 concrete and garage floor paint is an easy way to improve the appearance of what could become your favorite space!

DRYLOK E1 is a ready-to-use, 1-part epoxy floor paint which is formulated using **Advanced Epoxy Technology** for the ultimate in durability. It provides an easy to clean showroom-quality finish. In fact, E1 is comparable to a 2-part epoxy without the mixing and messy clean-up. E1 is as easy as applying ordinary house paint and has no strong odors or complicated mixing instructions. Best of all, clean-up is with soap and water.

E1 is resistant to hot tire marks/pick-up, chemicals, oil, grease and gasoline stains. This epoxy formula is a durable, UV-resistant, semi-gloss finish that resists scuffing, peeling, blistering and fading. Perfect for both interior and exterior high-traffic areas including concrete floors, garage floors, basement floors, shop floors, carports, walkways, driveways and patios.

**IMPORTANT:** Floors that are subjected to hydrostatic pressure (water seeping from underneath the floor) or are continually damp cannot be satisfactorily painted with any paint or coating. To determine if you have a moisture problem on the floor make this simple test: Tape a 12" x 12" piece of aluminum foil tightly on all four edges to prepped surface. Remove it after several days. If the floor side of the foil is wet, you have seepage. If the room side is wet, it's condensation. Use a dehumidifier. Remember, both problems can occur at the same time.



Tightly tape a piece of aluminum foil.

#### Surface Preparation

Proper surface prep is essential to product performance. Surface should be clean, **dry**, sound and free of dirt, dust, oil, wax and grease.

- 1 CLEAN** Remove dirt, oil and grease stains with DRYLOK Cleaner & Degreaser or other suitable concrete cleaner.
- 2 ETCH** Concrete is either broom finished or smooth troweled. A clean, broom finished surface is ready to paint. Smooth troweled, extremely smooth concrete will need to be etched or abraded for proper E1 Floor Paint adhesion. There are two methods to prepare smooth troweled concrete – Acid Etching or Mechanical Profiling. **Acid Etching** dissolves certain minerals in the top layer of concrete creating a more porous surface for improved adhesion. Use DRYLOK Liquid Etch and treat the surface until it has the texture of medium grit sand paper. **Mechanical Profiling** utilizes a concrete sander or abradar to roughen up the concrete profile to the proper texture. To test surface porosity once etched or abraded, sprinkle a few drops of water onto the concrete. If the water beads or doesn't penetrate additional prep is needed.
- 3 RINSE** Rinse thoroughly. Check to ensure that excess acid has been rinsed away by mixing 2 teaspoons of baking soda with 1 cup of water and sprinkle on concrete. If excess acid remains the baking soda will bubble and foam. Rinse again thoroughly and allow to dry thoroughly. Let dry at least 72 hours.  
**Note:** If using a power washer to clean the surface, once dry, use the "foil test" described above to make certain residual moisture is not trapped in the concrete and the surface is thoroughly dry.
- 4 APPLY** Air and surface temperatures must be above 50°F during application and drying. Apply two coats of DRYLOK E-1 Epoxy Floor Paint using a 3/8" nap roller or a nylon/polyester brush. Allow the first coat to dry for about 4 hours before applying the second coat.

#### Coverage

Depending on surface porosity, one gallon will cover up to 300-400 square feet.

#### Dry Time

DRYLOK E1 may be subject to light usage after 4 hours, heavy usage after 24 hours. Wait 5 days before subjecting to automobile traffic.

Detailed preparation and application instructions are on all product labels. FOLLOW ALL LABEL INSTRUCTIONS CAREFULLY!

**MADE IN THE USA**

**UGL**® UNITED GILSONITE LABORATORIES  
P.O. BOX 70, SCRANTON, PA 18501 • JACKSONVILLE, IL • JACKSON, MS • DAYTON, NV