



INTERIOR
EXTERIOR



DEKS OLJE® D.2

HIGH GLOSS OIL VARNISH

Product description

DEKS OLJE® D.2 is a varnish like, tough, flexible and durable finish that enhances the natural beauty of the wood. Easy to maintain and apply the more coats of DEKS OLJE® D.2 applied the higher the gloss finish. Unlike traditional varnishes DEKS OLJE® D.2 will not craze or blister and because of DEKS OLJE® D.1*'s penetrating qualities will not peel or flake as water is unable to get in to the wood.

Properties

- Flexible film that does not craze, peel or flake.
- High gloss finish.
- Highly transparent varnish – enhances the natural beauty of the wood.
- Long term protection.
- No sanding between coats.
- Easy maintenance.
- Easy repair, no stripping.

Basic uses

- Hardwoods and Exotic hardwoods - Oak, Chestnut, Ash, Teak, Ipe, Mahogany, Bangkirai...
- Softwoods - Pine, Spruce, Larch...
- New or weathered wood.
- Exterior - Garden furniture, window and door frames, gates...
- Interior - Panelling, doors, windows, joinery...
- Marine - All applications above waterline (Handrails, Wheel houses, trim...).
- Horizontal & vertical surfaces.

Technical data

Finish: Gloss.

Vehicle type: Alkyd-Urethane Resins.

Solvent type: Solvent.

Viscosity: Semi-Fluid.

Specific gravity: 0,910 ± 0,05 (20°C).

Physical state: Liquid.

Solid content: 56 % ± 5.

Flash point: > 60°C.

Shelf life: 2 years in original unopened packaging.

Container size: 1 L, 2.5 L, 20 L.

Colour: Amber.

Dry time: 12-24 hours per coat, depending on temperature and humidity.

Setting up time before use: 3 days.

VOC: EU limit value for this product (cat. A/e) 400 g/l (2010). This product contains max. 399 g/l.

Application tools

Brush, Roller.

Good application practice

Cover everything you do not wish to paint.

Apply between 8°C and 35°C.

Do not apply in direct sunlight or on to hot surfaces.

Surface preparation	<u>New wood:</u> All new wood must be treated with DEKS OLJE® D.1*. <u>Weathered wood previously treated with DEKS OLJE® D.1*:</u> Surfaces must be clean, dry and free of all surface contamination. Clean and restore DEKS OLJE® D.1* that has lightened to a grey finish, with NET-TROL®*, before applying DEKS OLJE® D.2. <u>Wood already treated with DEKS OLJE® D.2:</u> See maintenance.
Application	DO NOT THIN. USE AS IS. Apply 6 coats of DEKS OLJE® D.2 allowing a minimum of 12 hours between coats. All coats should be applied within 1 month. Sanding between coats is not required. For an extra high gloss finish, sand between the last 2 coats with 600 grit paper. Allow 3 days for DEKS OLJE® D.2 to set-up and dry, before putting the boat in service.
Coverage	15 m² per litre. Actual coverage will vary depending on application method, type, texture and porosity of the wood.
Maintenance	Wash frequently with fresh water to remove salt and dirt. <u>Areas worn back to DEKS OLJE® D.1* treated wood:</u> Sand with 320 grit paper. Clean worn area with NET-TROL®*. Leave to dry. Top up DEKS OLJE® D.1*. Apply required number of DEKS OLJE® D.2 coats to bring up to level of existing finish. <u>Rough or abraded areas:</u> Wet sand surface using 320 grit paper and DEKS OLJE® D.1* as the lubricant. Wipe over with a clean, dry, lint free cloth and leave to dry 24 hours. Apply 2 coats (minimum) or more of DEKS OLJE® D.2 to restore the finish. <u>New full coat:</u> Wet sand the whole surface using 320 grit paper and DEKS OLJE® D.1* as the lubricant. Wipe over with a clean, dry, lint free cloth and leave to dry 24 hours. Apply 1 or 2 coats of DEKS OLJE® D.2 as desired.
Restrictions	DEKS OLJE® D.2 should only be applied to surfaces treated with DEKS OLJE® D.1* or previously finished with DEKS OLJE® D.2. Do not apply DEKS OLJE® D.2 in wet weather or late in the day when dew or fog may be expected. This may dull a newly set film causing it to blush - exposure to sunlight usually removes the discoloration. DEKS OLJE® D.2 is very slippery, especially when wet and we therefore do not recommend the use of it on decks and other areas where it will be walked on.
Clean-up	Clean all tools and equipment with white spirits while still wet. If allowed to dry, remove with paint stripper. Wipe up any drips or runs immediately with a cloth soaked in white spirits. Dried DEKS OLJE® D.2 may be removed with DILUNETT®*. Store and maintain equipment as directed by manufacturer. Note: Any rags, steel wool etc soaked in DEKS OLJE® D.2 may spontaneously catch fire if improperly discarded. Rags, steel wool etc must be saturated with water after use or placed in a sealed, water filled metal container, before disposing with household waste.
Storage	Left over DEKS OLJE® D.2 should be transferred to a smaller, airtight, closed metal or glass container. Keep from freezing and high temperature.
General information	Every care is taken to ensure that the information provided in this technical data sheet is accurate. OWATROL INTERNATIONAL is unable to guarantee results as we have no control over the conditions under which our products are applied. For further advice and information please contact our technical department by email at info@owatrol.com or the local OWATROL Agent for your country. The information above is correct at the date of issue. All other OWATROL products named in this document should be used as per label instructions and the technical data sheet.
Safety	Keep out of the reach of children. Do not breathe vapours. Avoid contact with skin and eyes. If swallowed, do not induce vomiting: seek medical advice immediately and show the container or label. MSDS available at www.owatrol.com.
Issue date	April 2012.

* Same manufacturer