

DRYLOK® Natural Look Sealer

MANUFACTURER

UNITED GILSONITE LABORATORIES


MAILING: P.O. Box 70, Scranton, Pennsylvania, 18501

SHIPPING: 1396 Jefferson Avenue, Dunmore, Pennsylvania, 18509

TOLL FREE: 1-800-UGL-LABS (845-5227)

PHONE: 1-570-344-1202 • FAX: 1-570-969-7634

www.ugl.com



PRODUCT DESCRIPTION

DRYLOK Natural Look Sealer is the perfect choice to protect a surface without changing its natural appearance. Natural Look soaks into the surface providing an invisible protective coating.

As a sealer: DRYLOK Natural Look Sealer penetrates deep to seal and protect masonry against acids, alkalis, road salts, de-icing compounds, household cleaners, gasoline, oil and weathering. Protects against dusting, staining and spalling (surface cracking and pock marking).

As a concrete hardener: When applied to freshly poured concrete, after the surface has set for 24 hours and excess water has been removed, DRYLOK Natural Look Sealer will control water evaporation resulting in maximum concrete hardness.

- Natural looking penetrating sealer
- Ideal masonry primer, hardens concrete
- Minimizes concrete dusting, cracking and pock marking
- One coat protection

BASIC USES

SEALER: Specially formulated to protect interior and exterior masonry surfaces, including concrete driveways, basement floors, garage floors, concrete sidewalks, patios and terrazzo, brick and slate surfaces.

PRIMER: DRYLOK Natural Look Sealer will solidify the surface for painting when applied over powdery surfaces such as chalking masonry paint, sand blasted masonry and powdering mortar.

PRIMER-SEALER: Use Natural Look under latex, alkyd or polyurethane concrete floor paints or carpeting. For self adhesive floor tiles, check with tile manufacturer for adhesion compatibility.

CONCRETE HARDENER: Also use on freshly poured concrete to make concrete cure harder.

LIMITATIONS

DRYLOK Natural Look Sealer is not recommended as a waterproofer. For masonry walls subjected to hydrostatic pressure, use DRYLOK Masonry Waterproofers.

Do not use over silicone treated surfaces. Do not apply on asphalt surfaces.

TECHNICAL DATA

COMPOSITION:

Latex base

SHEEN:

Matte finish

% WEIGHT SOLIDS:

15% ± 0.5%

% VOLUME SOLIDS:

14% ± 0.5%

DENSITY (LBS./US GAL.):

8.4 ± 0.3

VISCOSITY:

11 seconds Ford #4 cup @75°F

pH:

8.1-8.5

COLORS:

N/A

DRY TIME:

- Light foot traffic: 2 hours
- Heavy traffic: 24 hours
- To recoat: 6 hours

Note: Maximum cure and dry time will be prolonged when slightly humid and damp, cool conditions prevail.

CLEAN UP:

Soap and water

Dispose of contaminated absorbent, container and unused contents in accordance with local, state and federal regulations.

COVERAGE (SQ. FT./US GAL.):

- 400 sq. ft./gal.

Note: Actual coverage will vary depending upon application method, surface texture and porosity.

RECOMMENDED FILM THICKNESS/COAT:

N/A

FLASH POINT:

N/A

SHELF LIFE:

5 Years

FREEZE/THAW:

Keep from freezing.

CONTAINER SIZES:

One gallon (US) and five gallon (US) containers

VOC

Does not exceed 250 g/L

TINTING

N/A

SURFACE PREPARATION

Remove all dirt, wax, dust, mildew, and loose or scaling material with a scraper, wire brush or stiff bristle brush. Grease, wax and oil should be removed by scrubbing with DRYLOK CONCRETE CLEANER & DEGREASER according to manufacturer's directions or use a heavy duty detergent in warm water. Rinse thoroughly with clean water. Allow to dry. If using a pressure washer, do not use on a pressure setting



DRY TIME:
2 Hours



CLEAN-UP:
Soap and Water



COVERAGE:
1 Coat



SPREAD RATE:
400 Sq. Ft./Gallon

above 1750 psi to avoid damaging the concrete. Remember, concrete acts like a concrete sponge, pressure washing and general cleaning may trap residual moisture in the concrete.

To check for trapped moisture, tape a 12" x12" piece of 3 mil plastic or aluminum foil tightly on all four edges to the surface. Remove it after 24 hours. If the floor side of the plastic or foil is damp, allow additional drying and repeat the test.

EFFLORESCENCE a white, powdery crystal-like deposit visible on the masonry surface, should be removed.

DRYLOK ETCH or muriatic acid, used according to manufacturer's directions, are effective efflorescence removal agents. All masonry surfaces are subject to occurrences of efflorescence.

Properly prepared concrete should look and feel like medium grit sandpaper. If concrete remains smooth, repeat etching procedure.

Test concrete porosity by sprinkling a few drops of water onto the surface in several areas. If the water is readily absorbed, you are ready to paint. If it beads or lays on the surface additional cleaning and etching is needed. Rinse thoroughly with clean water and allow to dry for 24 hours.

NOTE: Rinse etching solutions thoroughly. Etching solutions allowed to dry on masonry surfaces prevent proper curing of the DRYLOK finish coat and may result in the DRYLOK NATURAL LOOK SEALER appearing milky when dry.

Patch all holes and cracks with DRYLOK CONCRETE PATCH or a suitable cement based patching compound. Be sure to smooth the patch evenly. Allow the patched area to dry thoroughly.

WARNING

If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead

exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

APPLICATION

Apply only when air and surface temperature is above 50°F. DRYLOK Natural Look Sealer appears milky in the can- dries clear. Apply by brush, roller, spray or squeegee. Spread evenly- do not allow puddles or a heavy surface film to occur. Apply one coat using thin even strokes. Extremely porous surfaces may require a second coat. Allow 6 hours drying time between coats. Additional coats will cause surface to be slippery when wet.

On light-colored surfaces, some darkening may take place; test in an inconspicuous area to be sure darkening does not occur. May be applied to surfaces previously coated with a similar treatment. For best results, test a small area for proper adhesion prior to coating entire surface.

THINNING

Due to variations in porosity, when applied over flagstone, slate, terrazzo or dense, smooth concrete, thin DRYLOK Natural Look Sealer with equal parts of clean, lukewarm water. In addition, light colored concrete may darken unevenly due to variations in porosity. To minimize color variations, thin with water 1 to 1 and test on small area to see final effect.

CAUTION

Avoid prolonged contact with skin or breathing of spray mist.

KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. KEEP FROM FREEZING.

FIRST AID

EYES: Flush immediately with large amounts of water for at least 15 minutes. Consult a physician if irritation persists..

SKIN: Wash affected areas with soap and water. Consult a physician if irritation persists.


INGESTION: Seek medical attention. If individual is drowsy or unconscious, do not give anything by mouth. Place individual on the left side with head down. Contact a physician, medical facility or poison control center for advice about whether to induce vomiting..

INHALATION: Remove to fresh air.

For additional health and safety information please refer to the "Materials Safety Data Sheet".

SPECIFICATION

DRYLOK Natural Look Sealer meets A.S.T.M Specification C-309.



Natural Look Sealer

1 GAL. 2/Case22113
5 GAL. 1/Case22115

DISCLAIMER: This information is furnished without warranty, representation, inducement or license of any kind, except that it is accurate to the best of UGL's knowledge, or obtained from sources believed by UGL to be accurate, and UGL does not assume any legal responsibility for use or reliance upon same. Before using any product, read the label.