

SurfaPore™ C

Water-repellant agent for concrete surfaces, joints, stones, coatings, natural and artificial stones

Product Description

SurfaPore™ C is a water-based solution based on nanotechnology that achieves effective water-repellency and protection of structural surfaces. SurfaPore™ C penetrates porous substrates, capillaries and microcracks more effectively than conventional impregnation products. Unlike conventional products, which create a "plastic" protective film, SurfaPore™ C impregnates, waterproofs and protects surfaces by penetrating deep into the pores of cementitious materials without creating a film or change the surface appearance. In case of internal leakage or dampness, surfaces modified with SurfaPore™ C allow water to be transported only from the interior of the wall or building to the environment through evaporation. Surfaces modified with SurfaPore™ C is not affected by abrasion, stress or mechanical wear and are more resistant to solar radiation (UV radiation), therefore, they do not yellow and show prolonged durability. SurfaPore™ C is CE marked.

Recommended Use

Water-repellant agent for porous surfaces such as cement, stones, walls and joints. Ideal for walls and basements, roof, coating protection, preventing the growth of mould, moss & lichen, scale build-up, protecting joints and preventing rising damp in walls.

Key Benefits

- ☆ Highly active nanotechnology composition
- ☆ Permeability of the surface after application
- ☆ Non film forming
- ☆ Does not alter the appearance of the application surface
- ☆ Long lasting & UV resistant
- ☆ Odorless and environmentally friendly

NanoPhos S.A.

PO Box 519, Sci. & Tech. Park of Lavrio, 1st Km. Lavrio - Athens Ave., 19500 Lavrio, Greece
T. (+30) 22920 69312 | F. (+30) 22920 69303 | E. info@nanophos.com | W. www.NanoPhos.com

SurfaPore™ C

Water-repellant agent for concrete surfaces, joints, stones, coatings, natural and artificial stones

Technical Specifications

Type	□ Aqueous suspension
Color	□ Milky White
Density	□ $1.00 \pm 0.05 \text{ g/cm}^3$
Application Temperature	□ From +5°C to +35°C
pH	□ 5.5 ± 0.5
VOC (Volatile Organic Compounds)	□ $<0.1 \text{ g/L}$
Flowtime (Ford cup No 4)	□ 11.9sec @20°C
Moisture absorption at low pressure (RILEM Test Method 11.4)	□ 0 cm^3 (19 cm^3 reference sample)
Capillary water absorption (EN 1015-18:2003)	□ $C_m=0.08 \text{ kg}/(\text{m}^2 \cdot \text{min}^{1/2})$ ($C_m=0.33 \text{ kg}/(\text{m}^2 \cdot \text{min}^{1/2})$ for reference sample)

CE

0038

NanoPhos SA

Science & Technological. Park of Lavrio
19500 Lavrio, Attica, Greece

14

0038/CPR/PIR1407445/1

SurfaPore C

Concrete surface protection systems

Water-repellent impregnation

EN 1504-2

Depth of penetration: Class II $\geq 10 \text{ mm}$

Water absorption and alkali resistance:

- Absorption $<7.5\%$ compared to non-hydrophobic sample
- Absorption $<10\%$ after immersion in alkaline solution

Hazardous substances: According to Regulation 1907/2006 REACH, the product does not contain substances of high concern.

Drying rate factor: Class I $> 30\%$

NanoPhos S.A.

PO Box 519, Sci. & Tech. Park of Lavrio, 1st Km. Lavrio - Athens Ave., 19500 Lavrio, Greece

T. (+30) 22920 69312 | F. (+30) 22920 69303 | E. info@nanophos.com | W. www.NanoPhos.com

SurfaPore™ C

Water-repellant agent for concrete surfaces, joints, stones, coatings, natural and artificial stones

Surface Preparation

All surfaces must be clean, dry, free of dust, oils, salts, grease, rust and loose residue. New cement substrates or new masonry should have matured for more than 4 weeks before applying SurfaPore™ C.

Application Instructions

Shake well before use. SurfaPore™ C can be applied with roller, brush or spray without dilution. On highly absorbent surfaces, it is recommended to apply a second coat, within 3 hours of the first application. A small test is recommended before full application. Full curing is fully achieved in 24 hours after application.

Spreading Rate

8-10 m²/L, accordingly to the absorbance of surface application.

Storage

Store in well closed package, in a well-ventilated area, strictly at a temperature of 5°C to 35°C, away from sunlight and frost. Inclement storage conditions may affect product quality.

Health & Safety

Read the label of the product before use. Safety Data Sheet is available through NanoPhos' website www.NanoPhos.com or upon request by contacting NanoPhos through email: info@NanoPhos.com or by telephone: (+30) 2292069312.

Available Packaging

- 1L Plastic bottle
- 4L Plastic canister
- 10L Plastic canister
- 30L Plastic canister
- 1000L pallet tank

Disclaimer: The Technical Data Sheet recommendations for the use of NanoPhos' products are based on our scientific knowledge, laboratory studies and long-term experience. The information provided must be considered indicative and subject to constant review based on specific conditions and each practical application. The suitability of the product should be examined in each case for specific use and the end user bears full & exclusive responsibility for any side effects that may arise from the incorrect use of the product. The present edition of this technical datasheet automatically cancels any previous one concerning the same product. For more information please contact NanoPhos: info@NanoPhos.com

SurfaPore™ logo is a registered trademark of NanoPhos SA

NanoPhos S.A.

PO Box 519, Sci. & Tech. Park of Lavrio, 1st Km. Lavrio - Athens Ave., 19500 Lavrio, Greece
T. (+30) 22920 69312 | F. (+30) 22920 69303 | E. info@nanophos.com | W. www.NanoPhos.com